

OrcoSolve™ Solvent Dyes

Physical Properties & Resin Suitability

OrcoSolve™ solvent soluble dyes are applicable primarily aromatic hydrocarbons, oils, fats, waxes, wood stains and plastics

Page 1 of 2

Identification			Physical Properties				Resin Suitability							
OrcoSolve™	Shade		Chemical Character	Specific Gravity (g/cm3)	Melting Point (°C)	Light fastness in Polystyrene	Poly styrene	Rigid PVC	PolyPropylene	PMMA	ABS SAN	Poly ester	Poly carbonate	Poly amide
Nigrosine SB				1.30										
Nigrosine NB Base			Azine	1.25	142	5-6	x	x		x	x			
Blue B 200%			Anthraquinone	1.40	115	7	x	x		x		x		
Blue AP			Anthraquinone	1.25	169-173	7				x				
Blue N			Anthraquinone	1.72	208-216	7	x	x		x				
Blue ERO			Anthraquinone	1.37	142	5-7	x	x		x	x	x		
Blue 2B			Anthraquinone	1.30	240	7	x	x	x	x	x	x	x	x
Blue 2R			Anthraquinone	1.51	266-270	7-8	x	x		x	x			
Green B			Anthraquinone	1.35	213	6-7	x			x	x	x	x	x
Green 820			Anthraquinone		200	6-7	x	x			x	x	x	
Orange PER			Perinone	1.50	231-233	7-8	x	x		x	x	x	x	x
Orange Amber			Anthraquinone	1.16	195-199	7	x			x				
Red SBRO			Anthraquinone	1.20	198-202	5	x			x				
Red 4B			Azo	1.18	80	7-8	x			x				
Red MX			Azo	1.50	250	5-6	x		x	x				
Red 5			Anthraquinone	1.37	280	5-7	x	x	x	x	x	x	x	x
Red SBA			Anthraquinone	1.40	163-172	6-7	x	x		x	x	x	x	x
Red SBP			Perinone	1.40	316-318	6-7	x			x	x	x	x	x



Physical Properties & Resin Suitability for

OrcoSolve™ Solvent Dyes

Page 2 of 2

Red SBSE		Anthraquinone	1.40	176	7	x	x		x	x		x	x
Red SBSN		Anthraquinone	1.80	164-170	6-7	x	x		x	x		x	x
Red SBPN		Perinone	1.46	255	6	x			x	x	x	x	x
Red SBTO		Anthraquinone	1.40	236-251	3-5	x	x		x	x	x	x	x
Methyl Violet Base		Anthraquinone	1.35	180-183	6	x			x				x
Violet IRS		Anthraquinone	1.35	180-184	6	x			x			x	
Violet M		Anthraquinone	1.89	215	5-7	x			x	x	x		x
Violet R		Anthraquinone	1.47	186	7	x	x	x	x	x	x	x	x
Violet 3B		Anthraquinone	1.94	302	5-7	x	x		x		x		
Yellow EF		Azo	1.29	86		x			x				
Yellow SBC		Azo	1.03	176	6	x		x	x				
Yellow 4G		Monomethine	1.35	181	7	x	x		x	x		x	
Yellow G		Naphthalamide	1.49	264	7	x	x		x	x	x	x	
Yellow GS		Anthraquinone	1.30	182-186	6-7	x		x	x	x	x	x	x
Yellow TG		Anthraquinone	1.95	188	6-7	x			x		x	x	x
Fluorescent Green E		Anthraquinone	1.42	205	8	x			x			x	x
Fluorescent Orange FC		Thioxanthrene	1.73	310	7	x	x	x	x	x	x	x	x
Fluorescent Red G		Anthraquinone	1.70	144-146	5-7	x	x		x	x	x	x	x
Fluorescent Red 5B		Anthraquinone	1.00	296	7	x			x	x		x	x
Fluorescent Yellow 10GN		Anthraquinone	1.50	236-238	5-7	x			x	x	x	x	x
Fluorescent Yellow 3GF		Xanthene		220	7	x			x	x	x	x	x
Fluorescent Yellow FG		Naphthalamide	1.30	124-128	1-3	x			x				
Fluorescent Yellow 6G		Naphthalamide	1.86	230		x			x				

Information contained in this technical data sheet is up-to-date and correct to the best of Organic Dyes & Pigments' knowledge at the date of issue and are subject to change. As Organic Dyes & Pigments LLC cannot control or anticipate the conditions under which this product may be used, each user should review the information in specific context of the planned use. Organic Dyes & Pigments will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given.

Released: 03/25 RY

